

# Tuning order in the cuprate superconductors

Eugene Demler (Harvard)

Kwon Park

Anatoli Polkovnikov

Subir Sachdev

Matthias Vojta (Augsburg)

Ying Zhang


*Science* **286**, 2479 (1999).

Transparencies online at  
<http://pantheon.yale.edu/~subir>



Parent compound of the high temperature  
superconductors:  $La_2CuO_4$

Mott insulator: square lattice antiferromagnet




$$H = \sum_{\langle ij \rangle} J_{ij} \vec{S}_i \cdot \vec{S}_j$$

Ground state has long-range magnetic (Néel) order

Néel order parameter:  $\phi_\alpha = (-1)^{i_x+i_y} S_{i\alpha}$  ;  $\alpha = x, y, z$

$$\langle \phi_\alpha \rangle \neq 0$$

Introduce mobile carriers of density  $\delta$   
by substitutional doping of out-of-plane  
ions *e.g.*  $\text{La}_{2-\delta}\text{Sr}_\delta\text{CuO}_4$



Exhibits superconductivity below a high critical temperature  $T_c$

Superconductivity in a doped Mott insulator




BCS superconductor obtained by the Cooper  
instability of a metallic Fermi liquid

**Quantum numbers of ground state and low energy quasiparticles are the same, but characteristics of the Mott insulator are revealed in the vortices.**

S. Sachdev, *Phys. Rev. B* **45**, 389 (1992); K. Park and S. Sachdev *Phys. Rev. B* **64**, 184510 (2001).

STM measurement of J.E. Hoffman *et al.*, *Science*, Jan 2002.

Zero temperature phases of the cuprate  
superconductors as a function of hole density



Theory for a system with strong interactions:  
describe SC and SC+SDW phases by expanding in the  
deviation from the quantum critical point between them.

B. Keimer *et al.* Phys. Rev. B **46**, 14034 (1992).


S. Wakimoto, G. Shirane *et al.*, Phys. Rev. B **60**, R769 (1999).

G. Aeppli, T.E. Mason, S.M. Hayden, H.A. Mook, J. Kulda, Science **278**, 1432 (1997).

Y. S. Lee, R. J. Birgeneau, M. A. Kastner *et al.*, Phys. Rev. B **60**, 3643 (1999).

J. E. Sonier *et al.*, cond-mat/0108479.

C. Panagopoulos, B. D. Rainford, J. L. Tallon, T. Xiang, J. R. Cooper, and C. A. Scott, preprint.



S. Sachdev and J. Ye, *Phys. Rev. Lett.* **69**, 2411 (1992).

A.V. Chubukov, S. Sachdev, and J. Ye, *Phys. Rev. B* **49**, 11919 (1994)


## Outline

- I. Magnetic ordering transitions in the insulator ( $\delta=0$ ).
- II. Theory of SC+SDW to SC quantum transition
- III. Phase diagrams of above in an applied magnetic field  
Comparison of predictions with experiments.
- IV. Conclusions


# I. Magnetic ordering transitions in the insulator

Square lattice with first ( $J_1$ ) and second ( $J_2$ ) neighbor exchange interactions (say)


$$H = \sum_{i < j} J_{ij} \vec{S}_i \cdot \vec{S}_j$$



$$= \frac{1}{\sqrt{2}} (|\uparrow\downarrow\rangle - |\downarrow\uparrow\rangle)$$



Neel state



Spin-Peierls (or plaquette) state  
“Bond-centered charge order”

$J_2 / J_1$

N. Read and S. Sachdev,  
*Phys. Rev. Lett.* **62**, 1694  
(1989).

O. P. Sushkov, J. Oitmaa,  
and Z. Weihong, *Phys.*  
*Rev. B* **63**, 104420 (2001).

M.S.L. du Croo de Jongh,  
J.M.J. van Leeuwen,  
W. van Saarloos, *Phys.*  
*Rev. B* **62**, 14844 (2000).



See however L. Capriotti,  
F. Becca, A. Parola,  
S. Sorella,  
cond-mat/0107204 .

## Properties of paramagnet with bond-charge-order

Stable  $S=1$  spin exciton – quanta of 3-component  $\phi_\alpha$

$$\epsilon_k = \Delta + \frac{c_x^2 k_x^2 + c_y^2 k_y^2}{2\Delta}$$

$\Delta \rightarrow$  Spin gap




$S=1/2$  spinons are *confined*  
by a linear potential.

Transition to Neel state  $\Rightarrow$  Bose condensation of  $\phi_\alpha$

Develop quantum theory of SC+SDW to SC transition driven by  
condensation of a  $S=1$  boson (spin exciton)



# Framework for spin/charge order in cuprate



Confined, paramagnetic Mott insulator has

1. Stable  $S=1$  spin exciton  $\phi_\alpha$ .
2. Broken translational symmetry:- bond-centered charge order.
3.  $S=1/2$  moments near non-magnetic impurities

Theory of magnetic ordering quantum transitions in antiferromagnets and superconductors leads to quantitative theories for


- Spin correlations in a magnetic field
- Effect of Zn/Li impurities on collective spin excitations

## II. Theory of SC+SDW to SC quantum transition

Spin density wave order parameter for general ordering wavevector

$$S_{\alpha}(\mathbf{r}) = \Phi_{\alpha}(\mathbf{r}) e^{i\mathbf{K}\cdot\mathbf{r}} + \text{c.c.}$$

$\Phi_{\alpha}(\mathbf{r})$  is a complex field (except for  $\mathbf{K}=(\pi,\pi)$  when  $e^{i\mathbf{K}\cdot\mathbf{r}} = (-1)^{r_x+r_y}$ )



Associated “charge” density wave order

$$\delta\rho(\mathbf{r}) \propto S_{\alpha}^2(\mathbf{r}) = \sum_{\alpha} \Phi_{\alpha}^2(\mathbf{r}) e^{i2\mathbf{K}\cdot\mathbf{r}} + \text{c.c.}$$

J. Zaanen and O. Gunnarsson, *Phys. Rev. B* **40**, 7391 (1989).

H. Schulz, *J. de Physique* **50**, 2833 (1989).

O. Zachar, S. A. Kivelson, and V. J. Emery, *Phys. Rev. B* **57**, 1422 (1998).

## Action for SDW ordering transition in the superconductor

$$S = \int d^2 r d\tau \left[ |\nabla_r \Phi_\alpha|^2 + c^2 |\partial_\tau \Phi_\alpha|^2 + V(\Phi_\alpha) \right]$$


Similar terms present in action for SDW ordering in the insulator

Coupling to the  $S=1/2$  Bogoliubov quasiparticles of the  $d$ -wave superconductor

Trilinear “Yukawa” coupling

$$\int d^2 r d\tau \Phi_\alpha \Psi \Psi$$

is prohibited unless ordering wavevector is fine-tuned.




$$\kappa \sum_{\alpha} \int d^2 r d\tau |\Phi_{\alpha}|^2 \Psi^{\dagger} \Psi \text{ is allowed}$$

Scaling dimension of  $\kappa = (1/\nu - 2) < 0 \Rightarrow$  irrelevant.


## Neutron scattering measurements of dynamic spin correlations of the superconductor (SC) in a magnetic field

B. Lake, G. Aeppli, K. N. Clausen, D. F. McMorrow, K. Lefmann, N. E. Hussey, N. Mangkorntong, M. Nohara, H. Takagi, T. E. Mason, and A. Schröder, *Science* **291**, 1759 (2001).



Peaks at  $(0.5, 0.5) \pm (0.125, 0)$   
and  $(0.5, 0.5) \pm (0, 0.125)$

$\Rightarrow$  dynamic SDW of period 8



Neutron scattering off  $\text{La}_{2-\delta}\text{Sr}_\delta\text{CuO}_4$  ( $\delta = 0.163$ , *SC phase*)

at low temperatures in  $H=0$  (red dots) and  $H=7.5T$  (blue dots)


S. Sachdev, *Phys. Rev. B* **45**, 389 (1992), and N. Nagaosa and P.A. Lee, *Phys. Rev. B* **45**, 966 (1992), suggested an enhancement of dynamic spin-gap correlations (as in a spin-gap Mott insulator) in the cores of vortices in the underdoped cuprates. In the simplest mean-field theory, this enhancement appears most easily for vortices with flux  $hc/e$ .

D. P. Arovas, A. J. Berlinsky, C. Kallin, and S.-C. Zhang, *Phys. Rev. Lett.* **79**, 2871 (1997) suggested static Néel order in the cores of vortices (SC order “rotates” into Néel order in SO(5) picture) .

Using a picture of “dynamically fluctuating spins in the vortices”, the amplitude of the field-induced signal, and the volume-fraction of vortex cores ( $\sim 10\%$ ), Lake *et al.* estimated that in such a model each spin in the vortex core would have a low-frequency moment equal to that in the insulating state at  $\delta=0$  ( $0.6 \mu_B$ ).

**Observed field-induced signal is much larger than anticipated.**

### III. Phase diagrams in a magnetic field.




### III. Phase diagrams in a magnetic field.

#### A. Effect of magnetic field on onset of SDW in the insulator

$H$  couples via the Zeeman term

$$|\partial_\tau \Phi_\alpha|^2 \Rightarrow \left( \partial_\tau \Phi_\alpha^* - i \varepsilon_{\alpha\sigma\rho} H_\sigma \Phi_\rho \right) \left( \partial_\tau \Phi_\alpha - i \varepsilon_{\alpha\beta\gamma} H_\beta \Phi_\gamma \right)$$



Characteristic field  $g\mu_B H = \Delta$ , the spin gap

1 Tesla = 0.116 meV

Related theory applies to spin gap systems in a field and to double layer quantum Hall systems at  $\nu=2$

### III. Phase diagrams in a magnetic field.

(extreme Type II superconductivity)

#### B. Effect of magnetic field on SDW+SC to SC transition

Infinite diamagnetic susceptibility of non-critical superconductivity leads to a strong effect.

- Theory should account for dynamic quantum spin fluctuations
- All effects are  $\sim H^2$  except those associated with  $H$  induced superflow.
- Can treat SC order in a static Ginzburg-Landau theory


$$S_b = \int d^2 r \int_0^{1/T} d\tau \left[ |\nabla_r \Phi_\alpha|^2 + c^2 |\partial_\tau \Phi_\alpha|^2 + s |\Phi_\alpha|^2 + \frac{g_1}{2} (|\Phi_\alpha|^2)^2 + \frac{g_2}{2} |\Phi_\alpha^2|^2 \right]$$

$$S_c = \int d^2 r d\tau \left[ \frac{V}{2} |\Phi_\alpha|^2 |\psi|^2 \right]$$

$$Z[\psi(r)] = \int D\Phi(r, \tau) e^{-F_{GL} - S_b - S_c}$$
$$\frac{\delta \ln Z[\psi(r)]}{\delta \psi(r)} = 0$$

$$F_{GL} = \int d^2 r \left[ -|\psi|^2 + \frac{|\psi|^4}{2} + |(\nabla_r - iA)\psi|^2 \right]$$






*Strongly relevant* repulsive interactions between excitons imply that low energy excitons must be extended.

A.J. Bray and M.A. Moore, J. Phys. C **15**, L7 65 (1982).

J.A. Hertz, A. Fleishman, and P.W. Anderson, Phys. Rev. Lett. **43**, 942 (1979).

Dominant effect: **uniform** softening of spin excitations by superflow kinetic energy




Spatially averaged superflow kinetic energy

$$\sim \langle v_s^2 \rangle \sim \frac{H}{H_{c2}} \ln \frac{3H_{c2}}{H}$$

Tuning parameter  $s$  replaced by  $s_{eff}(H) = s - C \frac{H}{H_{c2}} \ln \left( \frac{3H_{c2}}{H} \right)$

# Main results

$T=0$




- All functional forms are exact.

# Structure of *long-range* SDW order in SC+SDW phase

Computation in a self-consistent “large  $N$ ” theory

Y. Zhang, E. Demler, and S. Sachdev, cond-mat/0112343





Dynamic structure factor

$$S(\mathbf{k}, \omega) = (2\pi)^3 \delta(\omega) \sum_{\mathbf{G}} |f_{\mathbf{G}}|^2 \delta(\mathbf{k} - \mathbf{G}) + \dots$$

$\mathbf{G} \rightarrow$  reciprocal lattice vectors of vortex lattice.

$\mathbf{k}$  measures deviation from SDW ordering wavevector  $\mathbf{K}$




## Neutron scattering measurements of static spin correlations of the superconductor+spin-density-wave (SC+SDW) in a magnetic field

Elastic neutron scattering off  $\text{La}_2\text{CuO}_{4+y}$

B. Khaykovich, Y. S. Lee, S. Wakimoto,

K. J. Thomas, M. A. Kastner,


and R.J. Birgeneau, cond-mat/0112505.



Solid line --- fit to : 
$$\frac{I(H)}{I(0)} = 1 + a \frac{H}{H_{c2}} \ln \left( \frac{3.0 H_{c2}}{H} \right)$$



$a$  is the only fitting parameter

Best fit value -  $a = 2.4$  with  $H_{c2} = 60 \text{ T}$



# Neutron scattering of $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ at $x=0.1$

B. Lake, G. Aeppli, *et al.*,  
Nature, Jan 2002.



Solid line - fit to : 
$$I(H) = a \frac{H}{H_{c2}} \ln\left(\frac{H_{c2}}{H}\right)$$

## Prediction of static CDW order by vortex cores in SC phase, with dynamic SDW correlations

“Spin gap” state in vortex core appears by a “local quantum disordering transition” of magnetic order: by our generalized phase diagram, charge order should appear in this region.

K. Park and S. Sachdev

Physical Review B **64**,  
184510 (2001).

In addition to fluctuating charge order modes detected in phonon scattering, it would also be useful to study systems in which the charge order is required to be static; in such situations, atomic-resolution scanning tunneling microscopy (STM) studies should yield much useful information on the microstructure of the charge order. Our physical picture implies that static charge order should be present in situations in which both magnetic and superconducting order have been suppressed (systems with one of these orders may only have fluctuating charge order). A convenient way to achieve this is by application of a strong magnetic field on underdoped samples.<sup>59</sup> A phenomenological theory of the phase diagram in a magnetic field has been provided recently in Ref. 60: the “normal” state in this phase diagram is a very

attractive candidate to bond-centered charge order. It would be especially interesting to conduct STM measurements on the strongly underdoped YBCO crystals that have become available recently,<sup>61</sup> after superconductivity has been suppressed by a static magnetic field. An alternative is to look for charge order in STM studies in which the superconductivity has only been locally suppressed, as is the case in the cores of vortices in the superconducting order.<sup>62,63</sup> However, the short-range nature of the suppression means that charge order is not required to appear, and may remain dynamic—this makes this approach less attractive. Recent indications<sup>64</sup> of mesoscale self-segregation of charge carriers in bulk samples also naturally raise the possibility of bond charge order in the lower density regions which (presumably) have suppressed superconductivity.

# Pinning of static CDW order by vortex cores in SC phase, with dynamic SDW correlations

A. Polkovnikov, S. Sachdev, M. Vojta, and E. Demler, cond-mat/0110329  
Y. Zhang, E. Demler, and S. Sachdev, cond-mat/0112343

Superflow reduces energy of dynamic spin exciton, but action so far does not lead to static CDW order because all terms are invariant under the “sliding” symmetry:

$$\Phi_{\alpha}(\mathbf{r}) \rightarrow \Phi_{\alpha}(\mathbf{r}) e^{i\theta}$$

Small vortex cores break this sliding symmetry on the lattice scale, and lead to a pinning term, which picks particular phase of the local CDW order

$$S_{\text{pin}} = \zeta \sum_{\text{All } \mathbf{r}_v, \text{ where } \psi(\mathbf{r}_v)=0} \int_0^{1/T} d\tau \left[ \Phi_{\alpha}^2(\mathbf{r}_v) e^{i\theta} + \text{c.c.} \right]$$

With this term, SC phase has static CDW but dynamic SDW

$$\langle \Phi_{\alpha}^2(\mathbf{r}) \rangle \neq 0 \quad ; \quad \langle \Phi_{\alpha}(\mathbf{r}) \rangle = 0$$

$$\delta\rho(\mathbf{r}) \propto \sum_{\alpha} \Phi_{\alpha}^2(\mathbf{r}) e^{i2\mathbf{K}\cdot\mathbf{r}} + \text{c.c.} \quad ; \quad S_{\alpha}(\mathbf{r}) = \Phi_{\alpha}(\mathbf{r}) e^{i\mathbf{K}\cdot\mathbf{r}} + \text{c.c.}$$


“Friedel oscillations of a doped spin-gap antiferromagnet”



# Pinning of CDW order by vortex cores in SC phase


Computation in self-consistent large  $N$  theory

$$\langle \Phi_\alpha^2(\mathbf{r}, \tau) \rangle \propto \zeta \int d\tau_1 \langle \Phi_\alpha(\mathbf{r}, \tau) \Phi_\alpha^*(\mathbf{r}_v, \tau_1) \rangle^2$$



Simplified theoretical computation of modulation in local density of states at low energy due to CDW order induced by superflow and pinned by vortex core

A. Polkovnikov, S. Sachdev, M. Vojta, and E. Demler, cond-mat/0110329




$$H = \sum_{ij} \left( -t_{ij} c_{i\sigma}^\dagger c_{j\sigma} + \Delta_{ij} c_{i\sigma}^\dagger c_{j,-\sigma}^\dagger + h.c. \right) + \sum_i \left[ v(\mathbf{r}_i) - \mu \right] c_{i\sigma}^\dagger c_{i\sigma},$$

$$v(\mathbf{r}) = v_1 \left\{ \cos[\mathbf{K}_{cx} \cdot (\mathbf{r} - \mathbf{r}_0)] + \cos[\mathbf{K}_{cy} \cdot (\mathbf{r} - \mathbf{r}_0)] \right\} e^{-|\mathbf{r} - \mathbf{r}_0|/\xi_c} \left( |\mathbf{r} - \mathbf{r}_0|^2 + 1 \right)^{-3/4}$$

**(E) STM around vortices induced by a magnetic field in the superconducting state**

J. E. Hoffman, E. W. Hudson, K. M. Lang, V. Madhavan, S. H. Pan,  
H. Eisaki, S. Uchida, and J. C. Davis, *Science*, Jan 2002




1Å spatial resolution  
image of integrated  
LDOS of  
 $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$   
( 1meV to 12 meV)  
at B=5 Tesla.

S.H. Pan *et al.* *Phys. Rev. Lett.* **85**, 1536 (2000).





# Vortex-induced LDOS integrated from 1meV to 12meV



J. Hoffman *et al*, Science, Jan 2002.

# Fourier Transform of Vortex-Induced LDOS map


K-space locations of vortex induced LDOS



K-space locations of Bi and Cu atoms

Distances in k-space have units of  $2\pi/a_0$   
 $a_0 = 3.83 \text{ \AA}$  is Cu-Cu distance

## Why does the charge order have period 4 ?




“Large  $N$ ” theory in region with preserved spin rotation symmetry

S. Sachdev and N. Read, *Int. J. Mod. Phys. B* **5**, 219 (1991).

M. Vojta and S. Sachdev, *Phys. Rev. Lett.* **83**, 3916 (1999).

M. Vojta, Y. Zhang, and S. Sachdev, *Phys. Rev. B* **62**, 6721 (2000).



See also J. Zaanen, *Physica C* **217**, 317 (1999),

S. Kivelson, E. Fradkin and V. Emery, *Nature* **393**, 550 (1998),


S. White and D. Scalapino, *Phys. Rev. Lett.* **80**, 1272 (1998).

# Effect of magnetic field on SDW+SC to SC transition

(extreme Type II superconductivity)

## Main results

$T=0$



Prospects for studying quantum critical point between SC and SC+SDW phases by tuning  $H$  ?